

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
3 February 2005 (03.02.2005)

PCT

(10) International Publication Number  
**WO 2005/010106 A2**

(51) International Patent Classification<sup>7</sup>: C09D 4/00

(21) International Application Number:  
PCT/US2004/022892

(22) International Filing Date: 15 July 2004 (15.07.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/489,052 22 July 2003 (22.07.2003) US

(71) Applicant (*for all designated States except US*): OM-  
NOVA SOLUTIONS INC. [US/US]; 175 Ghent Road,  
Fairlawn, OH 44333-3300 (US).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): SIZER, David  
[US/US]; 6602 Night Vista Drive, Parma, OH 44129 (US).  
HARSHBARGER, Richard [US/US]; 302 Archwood  
Ave, Munroe Falls, OH 44262 (US).

(74) Agent: BURLESON, David, G.; OMNOVA Solutions  
Inc., Legal Department, 175 Ghent Road, Fairlawn, OH  
44333-3300 (US).

(81) Designated States (*unless otherwise indicated, for every  
kind of national protection available*): AE, AG, AL, AM,  
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,  
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,  
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,  
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,  
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,  
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,  
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,  
ZW.

(84) Designated States (*unless otherwise indicated, for every  
kind of regional protection available*): ARIPO (BW, GH,  
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,  
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,  
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,  
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,  
GW, ML, MR, NE, SN, TD, TG).

Published:

— *without international search report and to be republished  
upon receipt of that report*

*For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.*



WO 2005/010106 A2

(54) Title: BASE-COAT IN-MOLD COATING

(57) Abstract: A coating composition for a fiber-reinforced plastic includes an aliphatic resin such as a saturated aliphatic ester intermediate polyurethane having terminal acrylate end groups, a hydroxyalkyl (meth)acrylate, a polyacrylate ester of an alkylene polyol, and a vinyl substituted aromatic.

## BASE-COAT IN-MOLD COATING

### BACKGROUND INFORMATION

[0001] The present invention relates to fiber-reinforced plastic (FRP) bearing thereon a composition that is suitable as a base coat in compression molding applications.

[0002] In-mold coating (IMC) compositions can be applied to FRP to provide a smooth surface and to reduce or eliminate substrate porosity. However, such coatings generally require painting to yield desirable end use properties.

[0003] A typical IMC composition involves the reaction product of an unsaturated fumarate polyester diol, a saturated polyester diol flexibilizer, a crosslinking aliphatic polyol having from 3 to 6 hydroxyl groups, a diisocyanate, and an ethylenically unsaturated crosslinking compound such as styrene; see, e.g., U.S. Pat. Nos. 4,189,517 and 4,222,929.

[0004] Other approaches are described in, for example, U.S. Pat. Nos. 4,331,735, 4,414,173, 4,515,710, and 5,084,353.

### SUMMARY OF THE INVENTION

[0005] The present invention provides a coating composition made from compounds that include a saturated polyester urethane acrylate and a saturated hydroxyalkyl (meth)acrylate. Inclusion of a polyacrylate ester of an alkylene polyol and a vinyl-substituted aromatic compound have been found to impart improved properties such as hardness, water resistance, low shrinkage, and adhesion to coatings made from such compositions. Optionally, a saturated (cyclo)aliphatic (meth)acrylate, which is thought to improve the flexibility of the coating, may be added, as well as one or more crosslinking agents.

[0006] The above components can be reacted in the presence of a peroxide initiator to chain extend and form a thermoset resin coating. The cured resin is clear unless pigmented. The present invention may be used as a finish coating in some applications, but the addition of a clear finish coat on its surface can be used to, e.g., enhance gloss. If a clear coating is not desired, various pigments, colorants, etc., can be added to yield a desired end color and opacity.

[0007] In the coating composition, certain compounds and resins, especially aromatic compounds such as aromatic polyesters and/or polyether urethane intermediates, aromatic epoxy-based resins, and the like, are avoided.

## 5 DETAILED DESCRIPTION OF ILLUSTRATIVE EMBODIMENTS

[0008] To achieve paint-like properties and clarity, the coating composition utilizes a saturated aliphatic polyester urethane which contains acrylate groups, generally at the terminal portions of the polymer. The polyester portion may be made from aliphatic dicarboxylic acids or aliphatic anhydrides and glycols. Such materials and their preparation are known and commercially available. The aliphatic dicarboxylic acids and anhydrides generally have from 1 to 15 carbon atoms and are desirably saturated (i.e., free of carbon-to-carbon double bonds) with specific examples including carbonic acid, malonic acid, succinic acid, glutaric acid, adipic acid, pimelic acid, suberic acid, azelaic acid, sebacic acid, the anhydride counterparts thereof, and the like, with adipic acid generally being preferred. Mixtures of two or more of the foregoing acids can be utilized as well. The polyols generally have from 2 to 15 carbon atoms and are saturated, with specific examples including ethylene glycol, propylene glycol, 1,3-butylene glycol, 1,4-butylene glycol, pentane diol, hexane diol, cyclohexanedimethanol dipropylene glycol, 2,2-dimethyl-1,3-propane diol, diethylene glycol, pinacol, and the like. Preferred glycols include ethylene glycol and neopentyl glycol.

[0009] The saturated aliphatic polyester intermediate generally has a number average molecular weight of from about 1000 to about 5000, and desirably from about 1500 to about 2500.

25 [0010] An aliphatic polyisocyanate can be reacted with the saturated polyester intermediate to form a polyurethane. The aliphatic portion is saturated and has from about 5 to 18 carbon atoms such as isophorone diisocyanate (IPDI), hexamethylene diisocyanate, cyclohexyl diisocyanate, and the like, with isophorone diisocyanate being preferred. The average equivalent ratio of NCO groups to OH end groups of the intermediate is from about 1.5 to about 2.5, desirably from about 1.9 to about 2.1, and preferably about 2.0. Such amounts are generally sufficient to form an isocyanate-terminated polyurethane prepolymer which then can be reacted with a hydroxyalkyl acrylate to form the saturated

30

polyester urethane containing (meth)acrylate generally at the terminal portions of the polymer chain. The acrylates can generally have a C<sub>2</sub>-C<sub>10</sub> ester portion such as ethyl, propyl, n-butyl, ethylhexyl, and the like, with ethyl and propyl being preferred. An example of a preferred material is CN963B80 polyester urethane acrylate diluted with 10-30% 1,6-hexanediol diacrylate (Sartomer Co., Inc.; Exton, Pennsylvania).

[0011] Polyester urethane acrylates in which one or both of the polyester precursors and polyisocyanates are unsaturated and/or aromatic preferably are not inasmuch as they may yield a coating with a tendency to yellow and degrade on aging. The polyester urethane acrylates are hence substantially free of such compounds, meaning that they generally contain unsaturated and/or aromatic components in an amount less than 25% (by wt.), desirably less than 10% (by wt.), preferably less than 5% (by wt.), and more preferably none at all, based upon the total weight of such polymer(s). Other compounds or monomers that preferably are avoided in the formation of the polyester urethane acrylates are polyethers and epoxy intermediates inasmuch as the same have been found to negatively affect weathering properties of coatings made therefrom. Thus, the polyurethane intermediate contains, based upon the total weight of the polyester urethane acrylates, less than 50% (by wt.); generally less than 25% (by wt.), preferably less than 10% (by wt.), more preferably less than 5% (by wt.), or none at all of polyether and/or epoxy groups.

[0012] Various compounds or components are utilized to react with the polyester urethane acrylate and form a thermoset resin. One component utilized is one or more hydroxyalkyl (meth)acrylates, wherein the alkyl group can contain from 1 to 10 carbon atoms, preferably from 1 to 5 carbon atoms, such as methyl, ethyl, butyl, etc., with propyl being preferred. The amount of such hydroxyalkyl (meth)acrylates is generally from about 2 to about 20 parts by weight (pbw), desirably from about 4 to about 16 pbw, and preferably from about 6 to about 12 pbw per 100 pbw of the polyester urethane acrylate. These compounds are utilized in addition to the hydroxyalkyl methacrylates that may be utilized to form the polyester urethane acrylate resins.

[0013] Another component is one or more vinyl-substituted aromatic compounds. These preferably contain a total of from 8 to 12 carbon atoms,

examples of which include styrene,  $\alpha$ -methyl-styrene, vinyl toluene, t-butyl styrene, and the like, with styrene being preferred. The amount of this component is generally from about 10 to about 100 pbw, desirably from about 30 to about 80 pbw, and preferably from about 45 to about 75 pbw per 100 pbw of polyester urethane acrylate.

[0014] Still another component is a polyacrylate, such as a triacrylate or preferably a diacrylate, ester of an alkylene polyol wherein the polyol has from about 2 to about 30 carbon atoms and preferably from about 2 to about 10 carbon atoms such as ethylene diol, butane diol, and the like. The ester moiety on the ends of the alkylene polyol is generally derived from (meth)acrylic acid or similar unsaturated carboxylic acid. Examples of preferred diacrylate esters of an alkylene diol include triethylene glycol di(meth)acrylate, (di)ethylene glycol di(meth)acrylate, tetraethylene glycol di(meth)acrylate, polyethylene glycol di(meth)acrylate, 1,3-butylene glycol di(meth)acrylate, 1,4-butanediol di(meth)acrylate, 1,6-hexanediol di(meth)acrylate, (propoxylated) neopentyl glycol di(meth)acrylate, polyethylene glycol (200, 400, 600) di(meth)acrylate, tripropylene glycol diacrylate, and alkoxyated aliphatic diacrylate. Examples of tri-functional acrylate esters of an alkylene polyol which can be optionally utilized include tris(2-hydroxyethyl) isocyanurate tri(meth)acrylate, (alkoxyated) trimethylolpropane tri(meth)acrylate, pentaerythritol triacrylate, and propoxylated glyceryl triacrylate. A preferred polyacrylate ester of an alkylene polyol for use in the present invention is 1,6-hexanediol diacrylate.

[0015] The amount of the diacrylate ester of the alkylene polyol is generally from about 10 to about 40 pbw, desirably from about 15 to about 35 pbw, and preferably from about 20 to about 30 pbw for every 100 pbw of the polyester urethane acrylate. The amount of the optional triacrylate ester of the alkylene polyol is low and generally is less than 10 pbw and preferably less than 5 pbw for every 100 pbw of the polyester urethane acrylate.

[0016] A coating composition derived from ingredients that include the foregoing generally is clear. Alternatively, the coating can be colored by utilizing a pigment, colorant, or the like in an amount to yield a desired color, tint, hue, or opacity. Pigments and pigment dispersions are known to the art and include, for



example,  $\text{TiO}_2$ , carbon black, phthalocyanine blue or red, chromium and ferric oxides, and the like.

[0017] The coating composition optionally can contain additional components such as a (cyclo)aliphatic (meth)acrylate wherein the (cyclo)aliphatic portion is saturated and contains from about 1 to about 50 carbon atoms, desirably from about 2 to about 20 carbon atoms. Representative examples include methyl (meth)acrylate, tetrahydrofurfuryl (meth)acrylate, isodecylmethacrylate, 2(2-ethoxy)ethoxy ethylacrylate, stearyl (meth)acrylate, lauryl (meth)acrylate, glycidyl methacrylate, isodecyl acrylate, isobornyl (meth)acrylate, tridecyl (meth)acrylate, and caprolactone acrylate, with isobornyl acrylate being preferred. The (cyclo)-aliphatic (meth)acrylate, when present, may optionally be added as a monomer diluent for the aliphatic polyester urethane acrylate component. Thus, Ebecryl™ 8411 aliphatic urethane diacrylate diluted 20% with isobornyl acrylate monomer (Surface Specialties Inc. of the UCB Group of companies; Smyrna, Georgia). The amount of the saturated (cyclo)aliphatic (meth)acrylate, when present, is generally from about 0.1 to about 25 pbw, desirably from about 0.1 to about 15 pbw, and preferably from about 0.5 to about 10 pbw per 100 total pbw of the polyester urethane acrylate.

[0018] The coating compositions of the present invention can also contain conventional additives, and fillers, etc., in conventional amounts. Thus, various cure inhibitors such as benzoquinone, (methoxy)hydroquinone, p-t-butylcatechol, and the like, can be utilized. Another additive is an accelerator such as cobalt octoate. Other classes of accelerators include zinc, or other metal, carboxylates. Various light stabilizers can be utilized such as, for example, the various hindered amines (HALS), substituted benzophenones, and substituted benztriazoles, and the like. Lubricants and mold release agents are generally utilized with specific examples including various metal stearates, such as zinc stearate or calcium stearate or phosphonic acid esters. Reinforcing fillers such as talc can be utilized. Talc has also been found to help promote adhesion of the in-mold coating composition to the fiber reinforced plastic substrate. Another additive is a hardener and thixotrope such as silica.

[0019] The polyester urethane acrylate and the other curing monomers or components of the present invention are chain extended through the utilization of

a free radical initiator such as a peroxide. Examples of suitable free radical initiators include tertiary butyl perbenzoate, tertiary butyl peroctoate in diallyl phthalate, diacetyl peroxide in dimethyl phthalate, dibenzoyl peroxide, di(p-chlorobenzoyl) peroxide in dibutyl phthalate, di(2,4-dichlorobenzoyl) peroxide in dibutyl phthalate dilauroyl peroxide, methyl ethyl ketone peroxide, cyclohexanone peroxide in dibutyl phthalate, 3,5-dihydroxy-3,4-dimethyl-1,2-dioxacyclopentane, t-butylperoxy(2-ethyl hexanoate), caprylyl peroxide, 2,5-dimethyl-2,5-di(benzoyl peroxy) hexane, 1-hydroxy cyclohexyl hydroperoxide-1, t-butyl peroxy (2-ethyl butyrate), 2,5-dimethyl-2,5-bis(t-butyl peroxy) hexane, cumylhydroperoxide, diacetyl peroxide, t-butyl hydroperoxide, ditertiary butyl peroxide, 3,5-dihydroxy-3,5-dimethyl-1,2-oxacyclopentane, and 1,1-bis(t-butylperoxy)-3,3,5-trimethyl cyclohexane and the like, and mixtures thereof. Another suitable free radical initiator is Luperox™ 575 t-amyl peroxy-2-ethylhexanoate (ATOFINA Chemicals, Inc.; Philadelphia, Pennsylvania).

[0020] Using mixtures of initiators to take advantage of, e.g., their different decomposition rates and times at different temperatures can be desirable. A preferred initiator is t-butyl perbenzoate. The peroxide initiator preferably is used in an amount sufficient to overcome the effect of any inhibitor and to cause curing of the ethylenically unsaturated compounds. In general, the peroxide initiator is used in an amount of from about 0.25 to about 5%, desirably from about 1 to about 4%, and preferably from about 1 to about 2%, by weight based on the total weight of all of the ethylenically unsaturated components employed in the coating compositions. The reaction of the polyester urethane acrylate with the curing components in the presence of the peroxide initiator is generally at a temperature of from about 90° to about 165°C (200°-330°F) and desirably from about 130° to about 155°C (270°-310°F).

[0021] The coating composition can be prepared as follows: the polyester urethane acrylate can be mixed with the vinyl-substituted aromatic compound(s) (e.g., styrene) and the hydroxyalkyl (meth)acrylate (e.g., hydroxypropyl methacrylate) and, if a saturated (cyclo)aliphatic (meth)acrylate such as isobornyl acrylate is included, this component is included in the mixture; after these compounds are mixed, fillers and additives such as cure inhibitors, light stabilizers, lubricants, etc., are added and mixed; the free radical peroxide initiator

typically is added last. (The polyacrylate ester of a polyol is typically present in the polyester urethane acrylate from the supplier.)

[0022] When a coating having a specific color is desired, one or more pigments, colorants, etc., can be utilized in suitable amounts. As known, often times various pigments or colorants are added with a carrier, for example, a polyester, so that they can be easily blended. Any conventional or suitable mixing vessel can be utilized, and the various components and additives mixed until the compounds are blended. Even if pigments are not contained in the blend, the mixture at this point is typically not clear. When desired, the mixed ingredients are coated onto a FRP such as a sheet molded compound as by injection molding with the IMC composition heated to a cure temperature. The cure temperature will vary depending upon the particular curative or peroxide utilized. Suitable cure temperatures generally range from about 90° to about 165°C (200°-330°F).

[0023] Upon cure or chain extension, the coating becomes clear and have very good properties such as high clarity, good adhesion to an FRP substrate such as a sheet molded compound, good hardness (e.g., a pencil hardness of at least H and desirably at least 2H), good scratch resistance, good water resistance, and good UV resistance. Such properties result in a coating which may be suitable as a finished surface in certain applications. However, a clear top coat can be applied to the surface after application of the coating to impart a high gloss to the composite, especially in those applications that demand high gloss finishes, such as automotive and other areas. That is, the coating composition when cured can be utilized as is with regard to some particular end use applications and does not need subsequent surface treatments, e.g., coating, another layer, etc., such as a paint, and the like. Nevertheless, a clear, high gloss top coat is preferred when a high gloss finish is desired.

[0024] The resulting coatings are generally flexible and can be utilized on any surface of a FRP substrate which can be a thermoplastic or a thermoset, on sheet molded compounds which are generally thermosets, on low pressure molding compounds (LPMC), and the like. Suitable end uses of finished or top-coated coating compositions of the present invention include various automotive parts such as spoilers, air dams, truck liners, patio furniture, satellite dishes, water craft components, and the like.



[0025] The invention will be better understood by reference to the following illustrative, non-limiting examples.

#### EXAMPLES

5 Formulas A and B, set forth below, were mixed and molded as follows:

##### Formula A

[0026] CN963B80™ polyester urethane acrylate (PUA), diacrylic ester of hexanediol, styrene, isobornyl acrylate and hydroxypropyl methacrylate (HPMA) in the indicated amount were added to a container and mixed thoroughly using  
10 mixing procedures conventional for organic resin solutions. Hydroquinone, cobalt octoate (12% in mineral oil), and zinc and calcium stearates were weighed into the resin solution prepared above, and again mixed thoroughly to dissolve the organics and disperse the stearates. Talc and Cab-O-Sil™ fumed silica (Cabot Corp.; Billerica, Massachusetts) were then weighed into the container with the  
15 organics and stearates, and mixed thoroughly to disperse the solids. All of the mixing occurred without external heating. A t-butyl perbenzoate initiator was added to the solution prepared above, and mixed thoroughly.

[0027] The FRP molding was prepared in a 40.6 cm × 40.6 cm chromed steel shear-edge mold from a conventional polyester SMC used commercially to  
20 prepare exterior automotive body panels. Molding conditions for the SMC were 149°C, a 70-second cure time, and 6.9 MPa pressure.

[0028] The coating was applied immediately following SMC cure by opening the mold, pouring in the coating on the FRP molding, and re-closing the mold. Cure conditions for the IMC were 149°C, a 60-second cure time, and 6.9 MPa  
25 pressure.

##### Formula B

[0029] Same as formula A, with the exception of the addition of isobornyl acrylate and a second aliphatic polyester urethane acrylate (Ebecryl™ 8411).

30 [0030] The formulations set forth below are based on a 600 g coating sample. Thus, the weight values provided below are the amount of each component added to obtain 600 g of the coating and will change if the amount of coating to be

produced is varied. Of course, the weight percent of each component will remain constant regardless of the amount of coating.

Table 1

	FORMULA A		FORMULA B	
	weight %	weight (g)	weight %	weight (g)
CN963B80 PUA	41.72	250.31	39.72	238.32
Ebecryl 8411 PUA	0.00	0.00	2.00	12.00
HPMA	2.86	17.18	2.86	17.18
cobalt octoate	0.39	2.31	0.39	2.34
hydroquinone	0.03	0.17	0.03	0.18
fumed silica	1.35	8.09	1.35	8.10
zinc stearate	0.51	3.08	0.51	3.06
calcium stearate	0.19	1.16	0.19	1014
talc	4.81	28.88	4.81	28.86
styrene	24.07	144.41	24.07	144.42
white paste*	24.07	144.41	24.07	144.42
<b>Total:</b>	<b>100%</b>	<b>600g</b>	<b>100%</b>	<b>600g</b>

5

\*50% by wt. each of CN963B80 PUA and TiO<sub>2</sub>.

[0031] Formulations A and B were tested with regard to various properties such as pencil hardness, tape adhesion and chip resistance. The results of these tests are set forth in Table 2.

10

Table 2

Test	Formula A	Formula B
Pencil Hardness	H	H
Tape adhesion (GM9071P)	100%	100%
Cross-hatch tape adhesion (Ford B1 106-1)	0	0
Chip resistance (GM9506P)	9	9

[0032] As apparent from the data of Table 2, coatings made from these compositions exhibit good properties. Addition of Ebecryl™ 8411 PUA (formula B) appears to increase the flexibility of the resulting coating, although the flexibility of the coating from formula A is quite sufficient for most applications.

15

What is claimed is:

1. A coating composition comprising;
  - a) a saturated aliphatic polyester urethane acrylate;
  - b) a hydroxyalkyl (meth)acrylate;
  - 5 c) a vinyl-substituted aromatic compound;
  - d) a polyacrylate ester of an alkylene polyol wherein said alkylene group has from 2 to 30 carbon atoms; and
  - e) optionally, a peroxide initiator.
- 10 2. The coating composition of claim 1 wherein at least one of the following is true: the number average molecular weight of the saturated polyester portion of said saturated aliphatic polyester urethane acrylate is from about 1000 to about 5000, said vinyl-substituted aromatic compound comprises from 8 to 12 carbon atoms, and the alkyl moiety of said hydroxyalkyl group comprises from 1 to  
15 10 carbon atoms.
3. The coating composition of any of claims 1 to 2 further comprising a (cyclo)aliphatic (meth)acrylate, wherein said (cyclo)aliphatic group is saturated and comprises from 1 to 50 carbon atoms.
- 20 4. The coating composition of any of claims 1 to 3 wherein, for every 100 parts by weight of said saturated aliphatic polyester urethane acrylate, the amount of said hydroxyalkyl (meth)acrylate is from 2 parts to 20 parts by weight, the amount of said vinyl-substituted aromatic compound is from 10 to 70 parts by  
25 weight, and the amount of said polyacrylate ester of an alkylene polyol is from 10 to 40 parts by weight.
5. The coating composition of claim 4 comprising, for every 100 parts by weight of said saturated aliphatic polyester urethane acrylate, from 6 to 16 parts  
30 by weight of said hydroxyalkyl (meth)acrylate, from 20 to 60 parts by weight of said vinyl-substituted aromatic compound, and from 15 to 35 parts by weight of said polyacrylate ester of an alkylene polyol.
6. The coating composition of any of claims 1 to 5 wherein at least one of  
35 the following is true: said saturated aliphatic polyester urethane acrylate is

prepared from ingredients comprising neopentyl glycol, ethylene glycol, adipic acid, isophorone diisocyanate, and hydroxyethyl (meth)acrylate, said hydroxyalkyl (meth)acrylate is hydroxypropyl methacrylate, said vinyl-substituted aromatic compound is styrene, and said polyacrylate ester of an alkylene polyol is a  
5 diacrylic ester of hexanediol.

7. The coating composition of any of claims 1 to 5 wherein a polyester portion of said saturated aliphatic polyester urethane acrylate is derived from at least a saturated carboxylic acid or an anhydride thereof and a saturated diol, and  
10 said urethane portion of said saturated aliphatic polyester urethane acrylate is derived from an aliphatic saturated polyisocyanate.

8. The coating composition of claim 7 wherein at least one of the following is true: said saturated carboxylic acid or anhydride has from 1 to 15  
15 carbon atoms, said saturated diol contains from 2 to 15 carbon atoms, and said saturated polyisocyanate is a C<sub>5</sub>-C<sub>18</sub> diisocyanate.

9. The coating composition of any of claims 1 to 5 wherein at least one of the following is true: said hydroxyalkyl (meth)acrylate comprises a C<sub>1</sub>-C<sub>5</sub> alkyl  
20 group and said polyol comprises a C<sub>2</sub>-C<sub>10</sub> alkylene group.

10. A process for applying a coating composition to a molded, fiber-reinforced plastic substrate and forming a coating thereon, comprising:  
a) into a die defining a mold cavity in which a molded substrate has been  
25 allowed to harden, injecting a metered amount of the coating composition of any of claims 1 to 9 and allowing said coating composition to contact at least a portion of a surface of said substrate;  
b) applying molding pressure to distribute said coating composition over said surface;  
30 c) maintaining said pressure while said material bonds to said surface and solidifies sufficiently to permit complete separation of said the component pieces of said die without disruption of the coating thus formed; and  
d) opening said die and removing said coated substrate from said cavity.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
3 February 2005 (03.02.2005)

PCT

(10) International Publication Number  
**WO 2005/010106 A3**

(51) International Patent Classification<sup>7</sup>: C09D 175/16,  
4/06, C08K 5/01, B05D 5/00

(21) International Application Number:  
PCT/US2004/022892

(22) International Filing Date: 15 July 2004 (15.07.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
60/489,052 22 July 2003 (22.07.2003) US

(71) Applicant (for all designated States except US): OM-  
NOVA SOLUTIONS INC. [US/US]; 175 Ghent Road,  
Fairlawn, OH 44333-3300 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): SIZER, David  
[US/US]; 6602 Night Vista Drive, Parma, OH 44129 (US).  
HARSHBARGER, Richard [US/US]; 302 Archwood  
Ave, Munroe Falls, OH 44262 (US).

(74) Agent: BURLESON, David, G.; OMNOVA Solutions  
Inc., Legal Department, 175 Ghent Road, Fairlawn, OH  
44333-3300 (US).

(81) Designated States (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,

AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,  
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,  
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,  
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,  
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,  
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,  
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,  
ZW.

(84) Designated States (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,  
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,  
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,  
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,  
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,  
GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the  
claims and to be republished in the event of receipt of  
amendments

(88) Date of publication of the international search report:  
6 May 2005

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: BASE-COAT IN-MOLD COATING

(57) Abstract: A coating composition for a fiber-reinforced plastic includes an aliphatic resin such as a saturated aliphatic ester intermediate polyurethane having terminal acrylate end groups, a hydroxyalkyl (meth)acrylate, a polyacrylate ester of an alkylene polyol, and a vinyl substituted aromatic.

WO 2005/010106 A3



# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US2004/022892

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09D175/16 C09D4/06 C08K5/01 B05D5/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09D B29C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 854 157 A (GENCORP INC; OMNOVA SOLUTIONS INC) 22 July 1998 (1998-07-22) Recipes A-C	1-9

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- \*Z\* document member of the same patent family

Date of the actual completion of the international search

14 February 2005

Date of mailing of the international search report

28/02/2005

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Miao, K

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US2004/022892

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0854157	A	22-07-1998	US 5777053 A 07-07-1998
			BR 9800325 A 01-06-1999
			CA 2224779 A1 17-07-1998
			DE 69806420 D1 14-08-2002
			DE 69806420 T2 20-02-2003
			EP 0854157 A1 22-07-1998
			JP 2975583 B2 10-11-1999
			JP 10204135 A 04-08-1998
			KR 275014 B1 15-12-2000